

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106 1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

## **TEST REPORT**

Client : Borg Manuf 2 Wella Way Somersby N		Test Number : Issue Date : Print Date : Order Number:	19-00232 22/05/20 11/06/201 095202	19
Sample Description	Clients Ref : Structaflor Particleboard Colour : Natural End Use : Flooring Nominal Composition : Timber, resin,w Nominal Mass per Unit Area/Density : Nominal Thickness : 19mm	/ax 660-700kg/m3		
AS/NZS 1530.3-1999	Methods for Fire Tests on Building Mate Part 3: Simultaneous Determination of I Flame Propagation, Heat Release and S	gnitability,	S	
	Face tested:	Face		
	Date tested:	22/05/2019		
		Standard Error	Mean	
	Ignition time	0.23	6.95	min
	Flame propagation time	10.4	115.7	sec
	Heat release integral	3.0	124.4	kJ/m²
	Smoke release, log d	0.0843	-1.3342	
	Optical density, d		0.0503	/ metre
	Number of specimens ignited:		6	
	Number of specimens tested:		6	
	Regulatory Indices:			
	Ignitability Index		13	Range 0-20
	Spread of Flame Index		4	Range 0-10
	Heat Evolved Index Smoke Developed Index		4	Range 0-10

168664

35776

© Australian Wool testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing - Chemical Testing - Mechanical Testing - Performance & Approvals Testing

: Accreditation No. : Accreditation No. : Accreditation No.

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Page 1 of 2

983

985

1356





Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106 1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

## **TEST REPORT**

Client :	Borg Manufacturing Pty Ltd	Test Number	:	19-002326
	2 Wella Way	Issue Date	:	22/05/2019
	Somersby NSW 2250	Print Date	:	11/06/2019
		Order Number : 0952		095202

These results only apply to the specimen mounted, as described in this report. The result of this fire test may be used to directly assess fire hazard, but it should be recognised that a single test method will not provide a full assessment of fire hazard under all fire conditions.

Each test specimen had an unattached backing of 4.5mm thick fibre reinforced cement board.

Each test specimen was clamped along all sides.

Specimens tended to flash before ignition. Ignition was based on the occurance of a single flash of flame which lasted longer than 10 seconds.

168664

35776

C Australian Wool testing Authority Ltd Copyright - All Rights Reserved



the Managing Director of AWTA Ltd.

Accredited for compliance with ISO/IEC 17025 - Testing - Chemical Testing - Mechanical Testing - Performance & Approvals Testing

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by

: Accreditation No. : Accreditation No. : Accreditation No.

983 985 1356

Page 2 of 2





SADY